



Eastech
亿科化学



聚合睿见 塑造无限

临时技术规格书

Provisional Technical Data Sheet

全球领先高性能聚合物材料制造商 & 客户一体化解决方案提供者

亿科化学有限责任公司

www.eastechchemical.com

ABS 产品资料 Product Information

产品牌号: B432/E

产品特性 Product features

Medium to high heat resistance

High stretch ratio

Good surface finish

✦ 中高耐热

✦ 高拉伸比

✦ 良好的表面光洁度

产品应用 Applications

Profiles

Multi-layer co-extruded sheets

Auto applications & Modification

✦ 型材

✦ 多层共挤板

✦ 汽车及改性

信息参数 Information parameters

性能 Properties	测试方法 Test Standard	测试条件 Test Condition	单位 Unit	典型值 Typical value ^[1,2]
物理性能 Physical properties				
密度 Density	ISO 1183	23°C	g/cm ³	1.04
熔体质量流动速率 Melt mass-flow rate(MFR)	ISO 1133	220°C/10kg	g/10min	4
机械性能 Mechanical properties(23°C/50% r. h.)				
拉伸屈服强度 Tensile strength at yield	ISO 527	50mm/min	MPa	45
屈服应变 Strain at yield	ISO 527	50mm/min	%	3.1
拉伸模量 Tensile modulus	ISO 527	1mm/min	MPa	2200
洛氏硬度 Rockwell hardness	ISO 2039/2	R Scale	/	110
弯曲强度 Flexural strength	ISO 178	2mm/min	MPa	68
弯曲模量 Flexural modulus	ISO 178	2mm/min	MPa	2100
悬臂梁缺口冲击强度 Izod notched impact strength	ISO 180/1A	23°C, 5.5J	kJ/m ²	19
热性能 Thermal properties				
维卡软化温度 Vicat softening temperature	ISO 306	50N, 50°C/h	°C	103
模塑收缩率 Molding shrinkage	ISO 294/4	23°C	%	0.4~0.7

[1]数据为典型值, 仅供参考, 不作为品质指标及其他用途的保证; The data are typical values for reference only and are not used as quality indicators or other purposes;

[2]不同颜色的产品其性能可能会不同。Different colors of products may have different properties.

ABS 产品资料 Product Information

产品牌号：B432/E

建议加工及干燥条件 Recommended processing & Drying conditions

- ❖ 干燥时间 Drying time 2~4h
- ❖ 干燥温度 Drying temperature 80~90℃
- ❖ 干燥设备 Drying equipment 热风式干燥机 Hot air dryer

注塑成型工艺 Injection molding process

相关条件 Related conditions

		典型值 Optimum	范围 Range
熔体温度	Melt Temp.	220℃	210~230℃
料筒温度	Barrel Temp.		
	后段, Rear	210℃	200~220℃
	中段, Middle	215℃	205~225℃
	前段, Front	220℃	210~230℃
	喷嘴, Nozzle	220℃	210~230℃
加工上限温度	Processing Temp. Upper Limit	260℃	
注射压力	Injection Pressure	40~100MPa	
注射速度	Injection Speed	40~80mm/s	
塑化背压	Plasticization Back Pressure	5~20MPa	
建议模具温度	Recommended Mold Temp.	40~80℃	

以上加工参数仅供参考，实际工艺参数应根据不同机型、不同模具以及不同产品等进行适当调整。
The above processing parameters are for reference only. Actual process parameters should be adjusted appropriately according to different models, different molds and different products.

本文本的数据与信息源自我们现在的认识与经验。如果将来有了新的认识和经验，不排除对本文本的信息与数据进行修改而不预先通知的可能。由于使用条件和适用法律可能因地因时而异，客户有责任确定本文件里的产品和产品信息是否适合客户使用，并确保自己的工作场地和处理产品的方式符合可适用的法律和其它政府法规。亿科化学对本文本信息不承担任何责任与义务，也未提供任何保证。在本文本中关于产品的可售性或某一特殊用途的可适用性的所有默示保证在此明确地予以排除。

The data and information in this text are based on our current knowledge and experience. If there are new understandings and experiences in the future, we reserve the right to modify the information and data in this text without prior notice. Since the conditions of use and applicable laws may vary by location and time, the customer is responsible for determining whether the products and product information in this document are suitable for the customer's use, and for ensuring that their workplace and the way they handle the products comply with applicable laws and other government regulations. Eastech Chemical does not assume any responsibility or obligation for the information in this text, nor does it provide any warranty. All implied warranties regarding the merchantability or fitness for a particular purpose of the products mentioned in this text are hereby expressly excluded.